

Application/ Control No.: 10/624,002  
 Examiner: GOLDBERG, C  
 CENTRAL FAX CENTER

OCT 05 2007


### IN THE CLAIMS

Please amend the claims of the present application under the provisions of 37 C.F.R. §1.121(c), as indicated below:

1. (Currently amended): A nitrate free grease composition for avoiding an abnormal peeling of a rolling surface of a bearing, said nitrate free grease comprising:

- a base oil,
- a thickener, and
- an additive,

wherein the base oil contains 20% by weight or more of alkyldiphenyl ether oil in the base oil, and has a kinetic viscosity of 20 to 150 mm<sup>2</sup>/s at 40 degree° C, and wherein the thickener is an aromatic diurea compound represented by the following formula (2)



where R<sub>2</sub> and R<sub>4</sub> are the same or different, and represent each an aromatic hydrocarbon group having 6 to 15 carbon atoms, and R<sub>3</sub> represents an aromatic hydrocarbon group having 6 to 15 carbon atoms, and is contained in an amount of 5 to 30% by weight based on the total amount of the base oil and the thickener, and wherein the additive contains as an essential component 0.05 to 10.5 parts by weight of a metal salt of a dibasic acid sodium sebacate based on 100 parts by weight of the base oil and the thickener, the metal salt of the dibasic acid being represented by the following formula:



Application/ Control No.: 10/624,002

Examiner: GOLOBOY, James C

where  $M_1$  and  $M_2$  represent the same or different alkali metal, and  $R_1$  represents aliphatic hydrocarbon group or an aromatic hydrocarbon group said grease containing no nitrate.

2. (Canceled)

3. (Previously presented): The grease composition as claimed in claim 1, wherein the base oil contains synthesized hydrocarbon oil.

4-6. (Canceled)

7. (Previously presented): The grease composition as claimed in claim 1, wherein each of the  $R_2$  and  $R_4$  is  $C_6H_4(CH_3)$ , and the  $R_3$  is  $-C_6H_4CH_2C_4H_4-$ .

8. -10. (Canceled)

11. (Currently amended): The grease composition as claimed in claim 1, wherein the additive comprises 0.05 to 5 parts by weight of an antioxidant in addition to the metal salt of the dibasic acid sodium sebacate based on 100 parts by weight of the base oil and the thickener.

12. (Previously presented): The grease composition as claimed in claim 11, wherein the antioxidant is selected from the group consisting of a sulfur-containing antioxidant, a phenol-based antioxidant and an amine-based antioxidant.

13. (Original): A grease composition sealed bearing, in which a sliding part of the bearing is sealed with the grease as claimed in claim 1.


14. (Currently amended): A nitrate free grease composition for avoiding an abnormal peeling of a rolling surface of a bearing, said nitrate free grease consisting essentially of:

- a base oil,
- a thickener, and
- an Additive,

Application/ Control No.: 10/624,002

Examiner: GOLOBOY, James C

wherein the base oil contains 20% by weight or more of alkylidiphenyl ether oil in the base oil, and has a kinetic viscosity of 20 to 150 mm<sup>2</sup>/s at 40°C, and wherein the thickener is an aromatic diurea compound represented by the following formula (2)



where R<sub>2</sub> and R<sub>4</sub> are the same or different, and represent each an aromatic hydrocarbon group having 6 to 15 carbon atoms, and R<sub>3</sub> represents an aromatic hydrocarbon group having 6 to 15 carbon atoms and is contained in an amount of 5% to 30% by weight based on the total amount of the base oil and the thickener, and

wherein the additive contains as an essential component 0.05 to ~~40~~ 5 parts by weight of a ~~metal salt of a dibasic acid sodium sebacate~~ based on 100 parts by weight of the base oil and the thickener, ~~the metal salt of the dibasic acid being represented by the following formula~~



~~where m1 and m2 represent the same or different alkali metal, and r1 represents aliphatic hydrocarbon group or an aromatic hydrocarbon group said grease containing no nitrate~~

wherein the additive contains 0.05 to 5 parts by weight of an antioxidant in addition to the sodium sebacate based on 100 parts by weight of the base oil and the thickener, and

wherein the antioxidant is selected from the group consisting of a sulfur-containing antioxidant, a phenol-based antioxidant and an amine-based antioxidant.